

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
14 October 2004 (14.10.2004)

PCT

(10) International Publication Number
WO 2004/088113 A1

(51) International Patent Classification⁷: **F02F 3/10**,
F02B 77/02, F16J 1/02

(21) International Application Number:
PCT/EP2004/050340

(22) International Filing Date: 22 March 2004 (22.03.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03291770.0 17 July 2003 (17.07.2003) EP

(71) Applicant (for all designated States except US): **SOREVI**
S.A. [FR/FR]; 5, Allée Skylab, Parc d'Ester, F-87068 Limoges (FR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **SAVALE, Jérémy**
[FR/FR]; 1, rue Palvezy, F-87000 Limoges (FR). **HERVÉ,**
Marc [FR/FR]; 55, rue Marcel Paul, F-87000 Limoges (FR). **VÉRINAUD, François** [FR/FR]; Bled, F-87270
Bonnac La Cote (FR).

(74) Agent: **MESSELY, Marc**; Bekaertstraat 2, B-8550 Zw-
evegem (BE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.


(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments
- upon request of the applicant, before the expiration of the
time limit referred to in Article 21(2)(a)

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PISTON WITH A SKIRT HAVING A LOW COEFFICIENT OF FRICTION



(57) Abstract: A piston (20) for an
internal combustion motor has a skirt
(22) with a surface (24), which is at
least partially polished and thereafter
coated with a coating (26) having a
hardness of greater than 8 GPa and
having a coefficient of friction of
less than 0.20. The piston has an
increased performance, a longer
lifetime and a reduced friction.

WO 2004/088113 A1

WO 2004/088113

PCT/EP2004/050340

PISTON WITH A SKIRT HAVING A LOW COEFFICIENT OF FRICTION.

Field of the invention.

5 The present invention relates to a piston of an internal combustion motor, and more particularly to an improvement of the skirt surface of the piston. The invention also relates to a method of treating the skirt surface of the piston and to a use of the piston.

Background of the invention.

10 On the one hand, pistons are widely known and used in internal combustion motors. The motors often operate with a frequency of several thousands rotations per minute at elevated temperatures. A lot of attention has been given to the working of those pistons, and more particularly to the reduction of friction of the piston inside the cylinder bore. Incremental reductions in friction or incremental
15 improvements in lubrication may increase substantially the efficiency of the motor.

20 On the other hand, coatings such as diamond-like coatings are well known in the art, amongst others, for their hardness, for their corrosion resistance and for their low coefficient of friction. Diamond-like coatings have been applied successfully on various automotive components such as valve heads, rods, shafts, piston rings, and cylinder heads...

25 Despite the widely spread use of pistons of internal combustion motors and despite the existence of hard coatings such as diamond-like coatings, application of hard coatings such as diamond-like coatings to the skirts of pistons has proved to be unsuccessful and
30 not in line with other applications of diamond-like coatings.

Summary of the invention.

It is an object of the invention to avoid the disadvantages of the prior art.

35 It is a further object of the invention to reduce the friction of a working piston of an internal combustion motor.

It is another object of the invention to reduce the need for an additional lubricant.

WO 2004/088113

PCT/EP2004/050340

-2-

It is still another object of the invention to increase the lifetime of a piston of an internal combustion motor.

It is yet another object of the invention to increase the performance of a piston of an internal combustion motor.

5

According to a first aspect of the present invention, there is provided a piston with a skirt. The skirt has a surface, which is at least partially polished and thereafter coated with a coating having a hardness of greater than 8 GPa and having a coefficient of friction of

10

less than 0.20.

The term hardness refers to a Vickers hardness.

The terms coefficient of friction refer to a friction coefficient as measured in a ball on disk test in dry circumstances. Reference is here made to ASTM G99 and to DIN 50 324. The friction test can be

15

performed by means of a multi-axis tribometer such as type TE 79 provided by Phoenix Tribology Ltd.

The part of the surface of the skirt is preferably polished until a surface with a flat surface morphology is obtained. The surface has

20

at least partially a ten-point mean roughness R_z of less than 1.0.

The ten-point mean roughness is determined as follows. A section of standard length is sampled from the mean line on the roughness chart. The distance between the peaks and valleys of the sampled line is measured in the y-direction. Then the average peak is

25

obtained amongst the five tallest peaks and the average valley is obtained amongst the five lowest valleys. The sum of these two values is then made and is expressed in micrometer (μm).

The part of the surface of the skirt is preferably polished until a surface roughness R_a of less than 0.15 has been reached.

30

The term R_a refers to the arithmetical mean roughness and its value is expressed in micrometer (μm). Preferably R_a ranges from 0.08 to 0.15, most preferably from 0.08 to 0.12, e.g. from 0.08 to 0.10.

35

The working of the invention can be explained as follows.

WO 2004/088113

PCT/EP2004/050340

-3-

5 A prior art piston skirt is provided with striations, ridges or small grooves. Generally the skirt surface has a ten-point mean roughness Rz about 7 to 8 and an arithmetical mean roughness Ra ranging from about 1 to about 5. The reason is that the skirt surface must retain the lubricating oil in order to allow for the sliding while reducing wear and friction. The relatively high surface roughness of the skirt functions as a reservoir for the lubricant.

10 So the skirt surface has an image of relatively high peaks and deep valleys. Coating the skirt with a hard coating such as a diamond-like carbon coating will not take away the existing roughness. Only the peaks will be covered with a hard coating that will make contact with any neighboring part. The surface area of the peaks is too small to make any effect.

15 The present invention departs from the generally accepted assumption that the skirt surface must be rough. The invention provides a polishing treatment prior to the coating so that the landscape of the skirt surface is flattened and that more working surface becomes available so that the effect of diamond-like carbon coatings is more pronounced.

20 The polishing treatment reduces the existing roughness and the reservoir available for the lubricant. However, this has not been considered as a disadvantage due to the self-lubricating properties of diamond-like coatings and due to a reduced need for extra lubrication.

25 JP-A-2000-320670 discloses a surface treatment method for a piston of a hydraulic pump or a hydraulic motor. To improve the sliding performance of the piston in a bore a surface hardening treatment is applied, thereafter the hardened layer is polished and the polished layer is coated with diamond-like carbon. The working circumstances of a hydraulic pump or hydraulic motor, however, are not that severe as in an internal combustion motor.

30

WO 2004/088113

PCT/EP2004/050340

-4-

According to the invention, preferably the hard coating is selected from the group of diamond-like carbon coatings, diamond-like nanocomposite coatings, and wolfram carbide coatings including any doped such coatings or a combination thereof.

5 The terms "wolfram carbide" coatings refers to wolfram carbide coatings as such but also to wolfram carbide coatings, which have been enriched with carbon or to WC/C coatings with an additional layer of carbon in order to reduce the friction.

10 For example, the hard coating may have two layers, a first layer of a diamond-like coating (DLC) and a surface layer of a diamond-like nanocomposite coating (DLN), which has a coefficient of friction, which is even lower than the coefficient of friction of DLC.

DLC coatings (a-C:H) are a mixture of sp² and sp³ bonded carbon atoms with a hydrogen concentration between 0 - 80%.

15 DLN coatings (a-C:H/a-Si:O) are commercialized under the trademark DYLYN® and comprise C, H, Si and O:

a-Si:O enhances high temperature stability, leads to lower friction & lowers films stress

a-C:H provides diamond-like properties.

20 An intermediate tie layer may be present between the polished skirt surface and the coating in order to increase the adhesion between the substrate of steel or aluminum and the hard coating.

25 In case there is an intermediate tie layer, the intermediate tie layer may be selected from a group consisting of diamond-like nanocomposite coatings, doped diamond-like coatings, TiN coatings, Ti (C,N) coatings, i-C coatings, wolfram carbide coatings, SiN coatings, CrN coatings or a combination hereof.

30 The hard coating on the polished skirt surface may have a thickness ranging from 1 micrometer to 10 micrometer, for example from 2 micrometer to 6 micrometer, e.g. about 4 µm.

35 According to a second aspect of the invention, there is provided a method of treating a piston, where the piston has a skirt.

WO 2004/088113

PCT/EP2004/050340

-5-

The method comprises the following steps:

- a) polishing at least partially the surface of the skirt;
- b) coating the thus polished surface with a coating having a hardness of greater than 8 GPa and having a coefficient of friction of less than 0.20.

Preferably the coating is done under vacuum, e.g. by means of a chemical vapor deposition (CVD) process, most preferably by means of a plasma assisted chemical vapor deposition (PACVD) process or by means of a mixed PVD/PACVD process.

The invention piston according to the first aspect of the invention or treated according to the second aspect of the invention may be used in an internal combustion engine.

Brief description of the drawings.

The invention will now be described into more detail with reference to the accompanying drawings wherein

FIGURE 1 shows a schematical drawing of a prior art embodiment of a piston;

FIGURE 2 shows a schematical drawing of a piston according to the first aspect of the invention.

Description of a prior art embodiment.

FIGURE 1 shows a prior art embodiment of a piston 10. The piston 10 has a skirt 12. An enlarged view of its surface 14 is also shown. This enlarged view shows a surface with roughnesses Ra ranging from 3 to 5 and even higher. The valleys between the peaks serve as reservoir for the lubricant and facilitate the mounting of the lubricant upwards. The coating of this prior art piston skirt with a hard coating does not lead to any substantial advantages. The reason is that any contact with e.g. the cylindrical bore is limited to the surfaces of the peaks, which are too small.

WO 2004/088113

PCT/EP2004/050340

-6-

Description of the preferred embodiments of the invention.

Embodiment 1

FIGURE 2 shows an embodiment of a piston 20 according to the invention. The piston 20 has a skirt 22 which may be out of steel or out of aluminum or out of titanium. The skirt 22 has been subjected to a polishing treatment preferably until its surface 24 obtains a roughness Ra of below 0.10. Thereafter a PACVD process deposits a hard diamond-like carbon coating with a thickness ranging between 1 μm and 6 μm , a hardness greater than 10 GPa and a coefficient of friction lower than 0.20.

The PACVD process mainly occurs as follows.

The pistons 20 with the polished skirt surfaces 24 are placed in a vacuum chamber.

A liquid organic precursor containing the elements C and H in suitable proportions is introduced in the vacuum chamber. A plasma is formed from the introduced precursor by an electron assisted DC-discharge using a filament with a filament current of 50-150 A, a negative filament bias DC voltage of 50-300 V and with a plasma current between 0.1 and 20 A and a composition is deposited on the piston skirt, to which a negative DC-bias or negative RF self-bias voltage of 200 to 1200 V is applied, in order to attract ions formed in the plasma.

The plasma generation and the vacuum deposition may be performed in one single chamber. The pistons 20 may be arranged on a rotatable support (in the upper part of the vacuum chamber) in a manner similar to that shown in US-patent 5,352,493. The base pressure in the vacuum chamber is 3×10^{-7} mbar and the typical working pressure is maintained at 1×10^{-4} to 1×10^{-3} mbar by diffusions pumps (controlled with throttle valves).

The piston skirts 22 can be cleaned by an in-situ (Ar-) plasma etching process prior to deposition. This plasma etching may last for 3 to

WO 2004/088113

PCT/EP2004/050340

-7-

30 minutes. The piston skirt temperature does generally not exceed 200 °C during the deposition process. .

5 A liquid precursor is preferably preheated above 30 °C before or during release in the vacuum chamber. The precursor is delivered to the vacuum chamber e.g. through a heat resistant porous body with a porosity of e.g. 30 to 50 %. The precursor can continuously be metered in small quantities through a tube, which delivers it as a vapor or a mist to the porous body. Otherwise the precursor can be
10 introduced in batch in an open reservoir, which is placed in the chamber before this is put to vacuum. This reservoir can be electrically heated prior to the start of the deposition process inside the chamber to form the vapor.

15 A bundle of alloyed Tungsten filaments is placed as a cathode typically at about -150 V (DC bias voltage) in front of the earthed porous body. The body itself, with the inlet tube for the precursor at the backside of the porous body may be mounted in the lower part of the chamber. The filament bundle is convexly bent, e.g. to a half
20 circle in a vertical plane and with a length of 15 to 30 cm. The current in the cathode filaments is preferably between 50 and 120 A (AC). The plasma current (measured between filament bundle and earthed porous body) can then typically amount to about 0.5 to 3 A. Preheating the precursor may offer the advantage that the current
25 needed afterwards in the cathode filaments (for generating the plasma) could be lowered.

The distance between the uppermost area of the bent cathode bundle and the piston skirt is at least about 20 cm. The deposition occurs
30 from bottom to top through attraction of the plasma ions by the substrate support, which is put to a negative RF self-bias voltage of typically about 400 V. Also the RF frequency is preferably much lower than that used according to US patent 5,352,493; viz. between 100 and 500 kHz and specifically about 200 to 300 kHz.
35

WO 2004/088113

PCT/EP2004/050340

-8-

Invention pistons for motors with two stroke cycles have shown an improved behavior with respect to existing prior art pistons. This improved behavior resulted from an increased lifetime or from an increased performance.

5

Embodiment 2

The following double coating has been deposited on a polished piston skirt 22:

10

- First a diamond-like carbon (DLC) coating of 3 μm ;
- Thereafter, a diamond-like nanocomposite (DLN) coating of 1 μm in order to profit from the usually lower coefficient of friction of DLN (e.g. less than 0.10 for DLN instead of less than 0.20 for DLC). Although lower than the hardness of DLC, the DLN topcoat still has a hardness higher than

15

10 GPa.

Embodiment 3

First some tie layers have been deposited on a polished piston skirt, and thereafter an I-C coating has been deposited:

20

- a TiN layer;
- a Ti (C,N) layer;
- an I-C coating

The coating has a hardness of more than 30 GPa and the coefficient of friction is less than 0.10.

25

Embodiment 4

First a tie layer of a silicon-nitrogen doped diamond-like carbon coating is deposited on a polished piston skirt. This coating has a good adhesion to the substrate. Thereafter a DLC top layer is deposited.

30

Embodiment 5

First a tie layer of DLN is deposited as tie layer on the polished piston skirt. Thereafter a DLC top coating is deposited.

35

WO 2004/088113

PCT/EP2004/050340

-9-

Embodiment 6

The initial rough surface of the piston skirt had following roughness parameters:

- Ra = 0.79 μm
- 5 - Rz = 6.32 μm

After polishing the piston skirt had a smooth planar surface with following roughness parameters:

- Ra = 0.02 μm
- Rz = 0.21 μm

- 10 The polished piston skirt has thereafter been covered with a DLC coating.

WO 2004/088113

PCT/EP2004/050340

-10-

CLAIMS

1. A piston (20) for an internal combustion motor,
said piston (20) comprising a skirt (22),
5 characterized in that
said skirt has a surface (24) which is at least partially polished
and thereafter coated with a coating (26) having a hardness of
greater than 8 GPa and having a coefficient of friction of less than
0.20.
- 10 2. A piston (20) according to claim 1, wherein said skirt (22) has a
surface with a flat surface morphology and which has at least
partially a ten-point mean roughness Rz of less than 1.0.
- 15 3. A piston (20) according to any one of the preceding claims,
wherein said skirt (22) has a surface, which has at least partially
an arithmetical mean roughness Ra of less than 0.15.
- 20 4. A piston (20) according to any one of the preceding claims
wherein said coating (26) is selected from the group of diamond-
like carbon coatings, diamond-like nanocomposite coatings,
wolfram carbide coatings or a combination thereof.
- 25 5. A piston (20) according to any one of the preceding claims
wherein an intermediate tie layer is present between said polished
surface and said coating.
- 30 6. A piston (20) according to claim 5 wherein said intermediate tie
layer is selected from a group consisting of diamond-like
nanocomposite coatings, doped diamond-like coatings, doped
diamond-like nanocomposite coatings, TiN coatings, Ti (C,N)
coatings, SiN coatings, CrN coatings, wolfram carbide coatings or
a combination hereof.

WO 2004/088113

PCT/EP2004/050340

-11-

7. A piston according to any one of the preceding claims wherein said coating has a thickness ranging from 1 micrometer to 10 micrometer.
- 5 8. A method of treating a piston (20) of an internal combustion motor,
said piston having a skirt (22),
characterized in that said method comprises the following steps:
a) polishing at least partially the surface of said skirt (22);
10 b) coating said at least partially polished surface (24) with a coating (26) having a hardness of greater than 8 GPa and having a coefficient of friction of less than 0.20.
- 15 9. A method according to claim 8, wherein said coating is done in vacuum.
- 20 10. A method according to claim 8, wherein said coating is done by means of a CVD process, a PVD process, a PACVD process or a mixed PVD/PACVD process.
11. Use of a piston according to any one of claims 1 to 7 in an internal combustion motor.

WO 2004/088113

PCT/EP2004/050340

1/1




Fig. 1




Fig. 2

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/050340

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 F02F3/10 F02B77/02 F16J1/02		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 F02F F02B F16J F01L		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, PAJ		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 14, 5 March 2001 (2001-03-05) & JP 2000 320670 A (KAYABA IND CO LTD), 24 November 2000 (2000-11-24) abstract; figure	1, 4, 5
Y	---	7, 8, 11
Y	WO 97/14555 A (ADVANCED REFRACTORY TECH) 24 April 1997 (1997-04-24) page 3, line 15 -page 11, line 6	7, 8, 11
A	page 21, line 4 -page 23, line 27; figures 2-6	1, 4, 6, 9, 10
A	US 5 249 554 A (GANGOPADHYAY ARUP K ET AL) 5 October 1993 (1993-10-05) page 2, line 23-32; figures column 3, line 48 -column 9, line 43 --- -/-	1, 4, 5, 8-10
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : 'A' document defining the general state of the art which is not considered to be of particular relevance 'E' earlier document but published on or after the international filing date 'L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) 'O' document referring to an oral disclosure, use, exhibition or other means 'P' document published prior to the international filing date but later than the priority date claimed 'T' later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention 'X' document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone 'Y' document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art '&' document member of the same patent family		
Date of the actual completion of the international search 19 August 2004		Date of mailing of the international search report 30/08/2004
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Luta, D

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP2004/050340

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 198 25 860 A (ELGAN DIAMANTWERKZEUGE GMBH &) 16 December 1999 (1999-12-16) column 3, line 61 -column 6, line 68 -----	2,3,9,10
A	US 4 666 786 A (KATO SHINJI ET AL) 19 May 1987 (1987-05-19) abstract -----	4,11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/050340

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 2000320670	A	24-11-2000	NONE	
WO 9714555	A	24-04-1997	AU 7371496 A WO 9714555 A1	07-05-1997 24-04-1997
US 5249554	A	05-10-1993	CA 2110563 A1 DE 69316575 D1 DE 69316575 T2 EP 0605992 A1 MX 9400261 A1	09-07-1994 26-02-1998 14-05-1998 13-07-1994 29-07-1994
DE 19825860	A	16-12-1999	DE 19825860 A1	16-12-1999
US 4666786	A	19-05-1987	JP 1870909 C JP 5083636 B JP 60197880 A DE 3503859 A1	06-09-1994 26-11-1993 07-10-1985 19-09-1985